



μ' (μ'')-Frequency




Initial permeability μ_i	25°C	2300±25%
Saturation magnetic flux density	3s(mT)	25°C 430
Remanent flux density	1194A/m	100°C 320
Coercivity	Hc(A/m)	25°C 26
		100°C 19
Tan δ/μ_i	25°C 10kHz	<2.7
Relative loss factor	at 25°C	($\times 10^{-6}$)

μ_i -Temperature





Cure temperature	T(°C)	180
Electrical resistivity	$\rho(\Omega\cdot m)$	3
Density	d(kg/m ³)	4.7×10 ³
Test core	toroid(mm)	

tan δ/μ_i -Frequency



ID : 19
H : 6

B-H



η_B - Temperature

